

Product Specification

BITUMEN

Characteristics	80/100	60/70
Specific Gravity at 27 0C min	0.98	0.99
Water percent by wt.max	0.2	0.2
Flash point, 0C	175	175
Softening point 0C	35-50	40-55
Penetration at 25 0C, 100 g 5 sec in 1/100 cm	80-100	60-70
Ductility at 27 0C, in cm. min	75	75
Loss on heating, percentage by wt.Max	1	1
Penetration of residue	60	60
Percent by wt. soluble in carbon di- sulphide, min	99	99

For more information please email us on info@corvalenergy.com